



BRANZ Appraised

Appraisal No. 605 [2008]

STOSTUCCO PLASTER CAVITY SYSTEM

Appraisal No. 605 (2008)

Amended 11 November 2015



BRANZ Appraisals

Technical Assessments of products for building and construction.



Stoanz Limited

72 Abel Smith Street
Wellington

Tel: 04 801 7794

Fax: 04 384 9828

Email: info@sto.co.nz

Web: www.sto.co.nz



BRANZ

1222 Moonshine Rd,
RD1, Porirua 5381
Private Bag 50 908
Porirua 5240,
New Zealand
Tel: 04 237 1170
branz.co.nz



Product

- 1.1 The StoStucco Plaster Cavity System is a cavity-based monolithic plaster wall cladding. It is designed to be used as an external wall cladding system for residential and light commercial type buildings where domestic construction techniques are used.
- 1.2 The system consists of a stainless steel lath fixed over timber battens to form the cavity. The coating system consists of an approximate 18 mm thick polystyrene bead saturated, polymer-modified, cement-based plaster applied to the lath, an approximate 2.5 mm thick coat of mesh reinforced plaster, and an approximate 1-3 mm thick coat of finish plaster. The plaster is then finished with a 100% acrylic exterior paint system. The top coat plasters can be finished to give different texture appearances.
- 1.3 The system incorporates a primary and secondary means of weather resistance [first and second line of defence] against water penetration by separating the cladding from the external wall framing with a nominal 20 mm wide cavity.

Scope

- 2.1 The StoStucco Plaster Cavity System has been appraised as an external wall cladding system for buildings within the following scope:
 - the scope limitations of NZBC Acceptable Solution E2/AS1, Paragraph 1.1; and,
 - constructed with timber framing complying with the NZBC; and,
 - with a risk score of 0-20, calculated in accordance with NZBC Acceptable Solution E2/AS1, Table 2; and,
 - situated in NZS 3604 Wind Zones up to, and including Extra High.
- 2.2 The StoStucco Plaster Cavity System has also been appraised for weathertightness and structural wind loading when used as an external wall cladding system for buildings within the following scope:
 - the scope limitations of NZBC Acceptable Solution E2/AS1, Paragraph 1.1; and,
 - constructed with timber framing complying with the NZBC; and,
 - situated in specific design wind pressures up to a maximum design differential ultimate limit state [ULS] of 2.5 kPa.
- 2.3 The StoStucco Plaster Cavity System must only be installed on vertical surfaces [except for tops of parapets, sills and balustrades, which must have a minimum 10° slope and be waterproofed in accordance with the Technical Literature].
- 2.4 The system is appraised for use with aluminium window and door joinery that is installed with vertical jambs and horizontal heads and sills. *[It is expected that the joinery will meet the requirements of NZS 4211 for the relevant Wind Zone, or wind pressure.]*

- 2.5 Installation of components and accessories supplied by Stoanz Limited and approved applicators must be carried out only by Stoanz Limited approved applicators.

Building Regulations

New Zealand Building Code (NZBC)

- 3.1 **In the opinion of BRANZ, the StoStucco Plaster Cavity System if designed, used, installed and maintained in accordance with the statements and conditions of this Appraisal, will meet the following provisions of the NZBC:**

Clause B1 STRUCTURE: Performance B1.3.1, B1.3.2 and B1.3.4. The StoStucco Plaster Cavity System meets the requirements for loads arising from self-weight, earthquake, wind, impact and creep. [i.e. B1.3.3 (a), (f), (h), (j) and (q)]. See Paragraphs 10.1 - 10.4

Clause B2 DURABILITY: Performance B2.3.1 (b) 15 years, B2.3.1 (c) 5 years and B2.3.2. The StoStucco Plaster Cavity System meets these requirements. See Paragraph 11.4

Clause E2 EXTERNAL MOISTURE: Performance E2.3.2. The StoStucco Plaster Cavity System meets this requirement. See Paragraphs 15.1-15.5.

Clause F2 HAZARDOUS BUILDING MATERIALS: Performance F2.3.1. The StoStucco Plaster Cavity System meets this requirement and will not present a health hazard to people.

- 3.2 This is an Appraisal of an **Alternative Solution** in terms of New Zealand Building Code compliance.

Technical Specification

- 4.1 System components and accessories supplied by Stoanz Limited are as follows:

Plasters

- **Levellite** is a polymer-modified, cement-based plaster comprising coarse sand, polypropylene fibres, polystyrene beads and adhesives. The plaster is supplied in 20 kg bags and mixed on site with clean water. It is trowel or pump-applied in two layers as a base coat approximately 18 mm thick.
- **StoArmat RFP** is a plasticiser free, tintable, ready-to-use, polymer-modified, cement free reinforcement plaster comprising granulated quartz sands, calibration grain, polypropylene fibre and additives. It is supplied in 23 kg pails, and after diluting with water as necessary and mixing, is ready for use. It is trowel-applied in a 2.5 mm thick layer followed by the embedment of fibreglass mesh reinforcement in the outer surface.
- **Stolit MP/K** is a plasticiser free, tintable, ready-to-use, polymer-modified, cement free finishing plaster with a 1, 1.5, 2 or 3 mm grain size. It is supplied in 25 kg pails and is trowel-applied to an approximate thickness of 1-3 mm.
- **Sto Flexyl** is a cementitious waterproof paste. It is used as a waterproofing membrane over plastered balustrades and fixing blocks. Sto Flexyl is supplied in 18 kg pails.

Paint System

- **StoColor Maxicryl** is a ready-to-use, tintable, acrylic exterior paint system for application over finishing plasters. It is supplied in 15 litre pails, and may be brush, roller or spray applied. The paint colour selected must have an LRV of 40% minimum regardless of gloss value.
- **StoLastic Color** is a ready-to-use, tintable, satin matt, acrylic exterior paint system paint for application over finishing plasters. It is supplied in 15 litre pails, and may be brush, roller or spray applied. The paint colour selected must have an LRV of 40% minimum regardless of gloss value.

Accessories

- **Stainless steel lath** - manufactured with AISI 304 stainless steel wire mesh into which an absorbent sheet of perforated chip paper is woven. The lath panels are supplied 700 mm high x 2400 mm wide.
- **Stainless steel corner beads** - manufactured with AISI 304 stainless steel wire. Supplied in 2950 mm lengths.

- **Reinforcing mesh** - alkali-resistant fibreglass mesh with a nominal mesh size of approximately 7 x 7 mm and an approximate weight of 165 g/m², or with a nominal mesh size of approximately 4 x 4 mm and an approximate weight of 165 g/m².
 - **Sto premeshed corners** - uPVC and fibreglass mesh corner mouldings.
 - **uPVC components** - foot tray incorporating a vermin tray acting as a ventilated cavity closure, head flashing, jamb flashing, sill flashing, soffit cap and control joint mouldings.
 - **Sto Joint Sealing Tape 2D** - Black, compressed polyurethane foam. The foam is coated on one side with a pressure sensitive adhesive, which is covered by a release paper. The tape is available 2 and 5 mm thick, expanding to maximum 6 and 12 mm thick after installation, and is supplied in rolls 15 mm wide and 18 and 9 m long respectively.
- 4.2 Accessories used with the system which are supplied by the approved applicator are:
- **Waterproof membrane tapes** - tapes covered by a valid BRANZ Appraisal for use as waterproofing membranes over tops of plastered balustrades, fixing blocks and the like.
 - **Flexible sealant** - sealant complying with NZBC Acceptable Solution E2/AS1, or sealant covered by a valid BRANZ Appraisal for use as a weather sealing sealant for exterior use.
- 4.3 Accessories used with the system which are supplied by the building contractor are:
- **Flexible wall underlay** - building paper complying with NZBC Acceptable Solution E2/AS1, Table 23, or breather-type membranes covered by a valid BRANZ Appraisal for use as wall underlays.
 - **Rigid wall underlay** - Plywood or fibre cement sheet complying with NZBC Acceptable Solution E2/AS1, Table 23, or rigid sheathing covered by a valid BRANZ Appraisal for use as rigid air barrier systems.
 - **Flexible sill and jamb flashing tape** - flexible flashing tapes complying with NZBC Acceptable Solution E2/AS1, Paragraph 4.3.11, or flexible flashing tapes covered by a valid BRANZ Appraisal for use around window and door joinery openings.
 - **Cavity battens** - 45 mm wide by 25 mm thick timber treated to Hazard Class H3.1.
 - **Cavity batten fixings** - 75 x 3.15 mm hot-dip galvanised flat head nails. *[Note: Hot-dip galvanising must comply with AS/NZS 4680.]*
 - **Stainless steel lath fixings** - 16g x 32 mm long Grade 304 stainless steel staples.
 - **Joinery head flashings** - as supplied by the joinery manufacturer or contractor.
 - **Sill diverter** - folded from aluminium to suit the window opening.
 - **Window and door trim cavity air seal** - air seals complying with NZBC Acceptable Solution E2/AS1, Paragraph 9.1.6, or self expanding, moisture cure polyurethane foam air seals covered by a valid BRANZ Appraisal for use around window, door, and other wall penetration openings.
 - **Inter-storey drained joint flashing and parapet cap flashing** - folded from aluminium or galvanised steel. Refer to NZS 3604, Section 4 or NZBC Acceptable Solution E2/AS1, Table 20 for durability requirements.

Handling and Storage

- 5.1 Handling and storage of all materials supplied by Stoanz Limited or the approved applicator, whether on or off site, is under the control of Stoanz Limited approved applicators. Dry storage must be provided on site for the fibreglass mesh and bags and pails of plaster mix. uPVC flashings and profiles must be protected from direct sunlight and physical damage, and should be stored flat and under cover. Liquid components must be stored in frost-free conditions.
- 5.2 Handling and storage of all materials supplied by the building contractor, whether on or off site, is under the control of the building contractor. Materials must be handled and stored in accordance with the relevant manufacturer's instructions.
- 5.3 Plaster must be used within the designated shelf life from the date of manufacture.

Technical Literature

- 6.1 Refer to the Appraisals listing on the BRANZ website for details of the current Technical Literature for the StoStucco Plaster Cavity System. The Technical Literature must be read in conjunction with this Appraisal. All aspects of design, use, installation and maintenance contained in the Technical Literature and within the scope of this Appraisal must be followed.

Design Information

Framing

Timber Treatment

- 7.1 Timber wall framing behind the StoStucco Plaster Cavity System must be treated as required by NZBC Acceptable Solution B2/AS1.

Timber Framing

- 7.2 Timber framing must comply with NZS 3604 for buildings or parts of a building within the scope limitations of NZS 3604. Buildings or parts of a building outside the scope of NZS 3604 must be to a specific design in accordance with NZS 3603 and AS/NZS 1170. In all cases studs must be at maximum 600 mm centres. Dwargs must be fitted flush between the studs at maximum 800 mm centres.
- 7.3 Timber framing and battens must have a maximum moisture content of 24% at the time of the cladding application. *[Note: If the cladding system is installed over framing or battens with a moisture content of greater than 24% problems may occur at a later date due to excessive timber shrinkage.]*

Stainless Steel Lath Set Out

- 7.4 The stainless steel lath must be installed perpendicular to the cavity battens in a staggered brick pattern. The lath is installed from the foot tray up with the lath labelling facing the applicator. The lath panels must be lapped by two sections at all vertical joints and one section at horizontal joints. The lath must be bent a minimum of 200 mm around internal and external corners and must be taken a minimum 200 mm past the line of all window and door joinery jambs, unless a vertical control joint is formed in line with the jamb. At the base of the wall, the lath and foot tray must hang 50 mm below the supporting framing.
- 7.5 Additional framing will be required at soffits, internal and external corners and window and door openings for the support and fixing of the cavity battens supporting the lath.

General

- 8.1 When the system is used for specifically designed buildings up to 2.5 kPa differential design ULS wind pressure, only the weathertightness aspects of the cladding and maximum framing centres, cavity batten and lath fixing centres are within the scope of this Appraisal. All other aspects of the building also need to be specifically designed and are outside the scope of this Appraisal.
- 8.2 Punchings in the foot tray provide a minimum ventilation opening area of 1000 mm² per lineal metre of wall in accordance with NZBC Acceptable Solution E2/AS1, Paragraph 9.1.8.3 [b].
- 8.3 The ground clearance to finished floor levels as set out in NZS 3604 must be adhered to at all times. At ground level, paved surfaces, such as footpaths, must be kept clear of the bottom edge of the cladding system by a minimum of 100 mm, and unpaved surfaces by 175 mm in accordance with the requirements of NZBC Acceptable Solution E2/AS1, Table 18.
- 8.4 At balcony, deck or roof/wall junctions, the bottom edge of the StoStucco Plaster Cavity System must be kept clear of any adjacent surface, or above the top surface of any adjacent roof flashing by a minimum of 35 mm in accordance with the requirements of NZBC Acceptable Solution E2/AS1, Paragraph 9.1.3.

- 8.5 All external walls of buildings must have barriers to airflow in the form of interior linings with all joints stopped for wind zones up to and including Very High, and rigid underlays for buildings in the Extra High wind zone and specifically designed buildings up to 2.5 kPa design differential ULS wind pressure. Unlined gables and walls must incorporate a rigid sheathing or an air barrier which meets the requirements of NZBC Acceptable Solution E2/AS1, Table 23. For attached garages, wall underlays must be selected in accordance with NZBC Acceptable Solution E2/AS1, Paragraph 9.1.3.4. Where rigid underlays are used, the cavity batten fixing lengths must be increased by a minimum of the thickness of the underlay.
- 8.6 Where penetrations through the StoStucco Plaster Cavity System are wider than the cavity batten spacing, allowance must be made for airflow between adjacent cavities. A minimum 10 mm gap must be left between the bottom of the vertical cavity batten and the flashing to the opening.
- 8.7 Where the system abuts other cladding systems, designers must detail the junction to meet their own requirements and the performance requirements of the NZBC. These details are outside the scope of this Appraisal.

Control Joints

- 9.1 Control joints must be constructed in accordance with the Technical Literature, and be provided as follows:
- Horizontal control joints - at maximum 5.4 m centres and at all inter-storey floor levels.
 - Vertical control joints - at maximum 5.4 m centres; aligned with any control joint in the structural framing; where the system abuts different cladding types, or where the system covers different structural materials.

[Note: Horizontal and Vertical Control joints must be located over structural supports. The design of vertical control joints where the system abuts different cladding types is outside the scope of this Appraisal and is the responsibility of the designer - see Paragraph 8.7.]

Inter-storey Junctions

- 9.2 Inter-storey drained joints must be constructed in accordance with the Technical Literature. Inter-storey joints must be provided to limit continuous cavities to the lesser of 2-storeys or 7 metres in height, in accordance with the requirements of NZBC Acceptable Solution E2/AS1, Paragraph 9.1.9.4 [b].

Structure

Mass

- 10.1 The mass of the StoStucco Plaster Cavity System is approximately 28 kg/m² at equilibrium moisture content, therefore it is considered a light wall cladding in terms of NZS 3604.

Impact Resistance

- 10.2 The system has adequate resistance to impact loads likely to be encountered in normal residential use. The likelihood of impact damage to the system when used in light commercial situations should be considered at the design stage, and appropriate protection such as the installation of bollards and barriers should be considered for vulnerable areas.

Wind Zones

- 10.3 The system is suitable for use in all Wind Zones of NZS 3604, up to, and including, Extra High where buildings are designed to meet the requirements of NZBC Acceptable Solution E2/AS1, Paragraph 1.1, or up to 2.5 kPa differential design ULS wind pressure where buildings are specifically designed.

Stainless Steel Lath Fixing

- 10.4 The lath must be fixed to the cavity battens at 150 mm centres on the parallel double reinforcing wires and around the wall perimeter. Two fixings are required at horizontal laps. Where the lath join is not over a batten, the panels must be clip tied together every 150 mm.

Durability

- 11.1 The StoStucco Plaster Cavity System meets the performance requirements of NZBC Clause B2.3.1 [b], 15 years for the cavity system and plaster finish, and the performance requirements of NZBC Clause B2.3.1 [c], 5 years for the exterior paint system.

Serviceable Life

- 11.2 The StoStucco Plaster Cavity System is expected to have a serviceable life of at least 30 years provided the system is maintained in accordance with this Appraisal, and the lath, fixings and plaster are continuously protected by a weathertight coating and remain dry in service.
- 11.3 Microclimatic conditions, including geothermal hot spots, industrial contamination and corrosive atmospheres, and contamination from agricultural chemicals or fertilisers can convert mildly corrosive atmosphere into aggressive environments for fasteners. The fixing of cavity battens and the stainless steel lath in areas subject to microclimatic conditions requires specific design in accordance with NZS 3604, Paragraph 4.2.4, and is outside the scope of this Appraisal.

Maintenance

- 12.1 Regular maintenance is essential to ensure the performance requirements of the NZBC are continually met and to ensure the maximum serviceability of the system.
- 12.2 Annual inspections must be made to ensure that all aspects of the cladding system, including the paint coating system, plaster, flashings and any sealed joints remain in a weatherproof condition. Any cracks, damaged areas or areas showing signs of deterioration which would allow water ingress, must be repaired immediately. Sealant, paint coatings and the like must be repaired in accordance with the instructions of Stoanz Limited.
- 12.3 Although the paint system is designed as a special dirt and algae resistant type, regular cleaning [at least annually] is still recommended to remove any grime, dirt and organic growth that may have accumulated, and to maximise the life and appearance of the paint system. Grime may be removed by brushing with a soft brush, warm water and detergent. The paint system must be recoated at approximately 8-10 yearly intervals in accordance with Stoanz Limited instructions.
- 12.4 Minimum ground clearances as set out in this Appraisal and the Technical Literature must be maintained at all times during the life of the system.

[Note: Failing to adhere to the minimum ground clearances given in this Appraisal and the Technical Literature will adversely affect the long term durability of the StoStucco Plaster Cavity System.]

Control of External Fire Spread

- 13.1 The StoStucco Plaster Cavity System has a peak heat release rate of less than 100 kW/m² and a total heat released of less than 25 MJ/m². In accordance with NZBC Acceptable Solution C/AS1 Table 5.1 the system is suitable for use on buildings with a SH Risk Group classification, at any distance to the relevant boundary. Refer to NZBC Acceptable Solutions C/AS2 – C/AS6, Paragraph 5.8.1 for the specific exterior surface finishes requirements for other building Risk Groups.

Prevention of Fire Occurring

- 14.1 Separation or protection must be provided to the StoStucco Plaster Cavity System from heat sources such as fire places, heating appliances, flues and chimneys. Part 7 of NZBC Acceptable Solutions C/AS1 – C/AS6 and NZBC Verification Method C/VM1 provide methods for separation and protection of combustible materials from heat sources.

External Moisture

- 15.1 The StoStucco Plaster Cavity System, when installed in accordance with this Appraisal and the Technical Literature, prevents the penetration of moisture that could cause undue dampness or damage to building elements.
- 15.2 The cavity must be sealed off from the roof and sub-floor space to meet code compliance with NZBC Clause E2.3.5.

- 15.3 The StoStucco Plaster Cavity System allows excess moisture present at the completion of construction to be dissipated without permanent damage to building elements to meet code compliance with NZBC Clause E2.3.6.
- 15.4 The details given in the Technical Literature for weather sealing are based on the design principle of having a first and second line of defence against moisture entry for all joints, penetrations and junctions. The ingress of moisture must be excluded by detailing joinery and wall interfaces as shown in the Technical Literature. Weathertightness details that are developed by the designer are outside the scope of this Appraisal and are the responsibility of the designer for compliance with the NZBC.
- 15.5 The use of StoStucco Plaster Cavity System where there is a designed cavity drainage path for moisture that penetrates the cladding, does not reduce the requirement for junctions, penetrations, etc to remain weather resistant.

Internal Moisture

- 16.1 The StoStucco Plaster Cavity System alone does not meet NZBC Acceptable Solution E3/AS1, Paragraph 1.1.1 [a]. Buildings must be constructed with an adequate combination of thermal resistance and ventilation, and space temperature must be provided to all habitable spaces, bathrooms, laundries and other spaces where moisture may be generated or may accumulate.

Water Vapour

- 16.2 The StoStucco Plaster Cavity System is not a barrier to the passage of water vapour, and when installed in accordance with this Appraisal will not create or increase the risk of moisture damage resulting from condensation.

Installation Information

Installation Skill Level Requirements

- 17.1 Installation and finishing of components and accessories supplied by Stoanz Limited and the approved applicator must be completed by trained applicators, approved by Stoanz Limited.
- 17.2 Installation of the accessories supplied by the building contractor must be completed by tradespersons with an understanding of cavity construction, in accordance with instructions given within the Stoanz Limited Technical Literature and this Appraisal.

System Installation

Building Underlay and Flexible Sill and Jamb Tape Installation

- 18.1 The selected building underlay and flexible sill and jamb tape system must be installed by the building contractor in accordance with the underlay and tape manufacturer's instructions prior to the installation of the cavity battens and the rest of the StoStucco Plaster Cavity System. Flexible building underlay must be installed horizontally and be continuous around corners. Underlay must be lapped 75 mm minimum at horizontal joints and 150 mm minimum over studs at vertical joints. Generic rigid sheathing materials must be installed in accordance with NZBC Acceptable Solution E2/AS1 and be overlaid with a flexible wall underlay. Proprietary systems shall be installed in accordance with the manufacturer's instructions. Particular attention must be paid to the installation of the building underlay and sill and jamb tapes around window and door openings to ensure a continuous seal is achieved and all exposed wall framing in the opening is protected.

Aluminium Joinery Installation

- 18.2 Aluminium joinery and associated head flashings must be installed by the building contractor in accordance with the Technical Literature. A 7.5-10 mm nominal gap must be left between the joinery reveal and the wall framing so a PEF rod and air seal can be installed after the joinery has been secured in place. The joinery must be spaced 22-23 mm off of the wall frame to allow the StoStucco Plaster Cavity System flashings to be installed.

Cavity Batten Installation

- 18.3 The cavity battens must be installed over the building wrap to the wall framing at maximum 300 mm centres where the studs are at 600 mm centres or at 400 mm centres when studs are at 400 mm centres. The cavity battens must be fixed in place to the studs with 75 x 3.15 mm hot-dip galvanised flat head nails at 300 mm centres with pairs of these nails into the top and bottom plates. Where the cavity battens are installed at 300 mm centres, the intermediate battens must be fixed with 75 x 3.15 mm hot-dip galvanised flat head nails into each dwang with pairs of nails into the top and bottom plates.

StoStucco Plaster Cavity System

- 18.4 Components and accessories supplied by Stoanz Limited and the approved applicator must be installed in accordance with the Technical Literature by Stoanz Limited approved applicators.
- 18.5 The StoStucco plaster system must only be applied when the air temperature is within the range of +5°C to 30°C.

Inspections

- 18.6 The Technical Literature must be referred to during the inspection of StoStucco Plaster Cavity System installations.

Health and Safety

- 19.1 Safe use and handling procedures for the components that make up the StoStucco Plaster Cavity System are provided in the relevant manufacturer's Technical Literature.

Basis of Appraisal

The following is a summary of the technical investigations carried out:

Tests

- 20.1 The following testing has been completed by BRANZ:
- BRANZ expert opinion on NZBC Clause E2 code compliance for StoStucco Plaster Cavity System was based on testing and evaluation of all details within the scope and as stated within this Appraisal. The StoStucco Plaster Cavity System was tested to NZBC Verification Method E2/VM1 [as contained within NZBC Clause E2, Amendment 4]. The testing assessed the performance of the foundation detail, window head, jamb and sill details, meter box head, jamb and sill details, vertical and horizontal control joints, internal and external corners and balustrade to wall junction with a plastered cap. In addition to the weathertightness test, the details contained within the Technical Literature have been reviewed, and an opinion has been given by BRANZ technical experts that the system will meet the performance levels of NZBC Acceptable Solution E2/AS1 for drained cavity claddings.
 - Wind face load testing for the StoStucco Plaster Cavity System. BRANZ determined design wind suction pressures, and by comparing these pressures with the NZS 3604 design wind speeds and AS/NZS 1170 pressure coefficients, the fixing requirements were determined for timber framed walls.
 - A racking test was completed to examine the performance of the StoStucco Plaster Cavity System when the system was subjected to both serviceability level and ultimate level seismic racking deflections, taken to be ±8 mm and ±36 mm respectively. The plaster system did not crack or show signs of damage for the entire test program.
 - Cone Calorimeter testing of the StoStucco Plaster System. The testing was carried out in accordance with AS/NZS 3837.

Other Investigations

- 21.1 Structural and durability opinions have been given by BRANZ technical experts.
- 21.2 Site visits have been carried out by BRANZ to assess the practicability of installation, and to examine completed installations.
- 21.3 The Technical Literature for the StoStucco Plaster Cavity System has been examined by BRANZ and found to be satisfactory.

Quality

- 22.1 The manufacture of the Levellite base plaster has been examined by BRANZ, including methods adopted for quality control. Details regarding the quality and composition of the materials used were obtained by BRANZ and found to be satisfactory. The quality control system of the Levellite plaster manufacturer has been assessed and registered as meeting the requirements of the Telarc Q-Based Code.
- 22.2 The manufacture of the Sto RFP Armat plaster, Stolit MP/K plasters, Sto Flexyl plaster, StoColor Maxicryl paint and StoLastic Color paint has not been examined by BRANZ, but details regarding the quality and composition of the materials used were obtained by BRANZ and found to be satisfactory. The quality management system of the manufacturer of these plasters and paint, Sto AG, has been assessed and registered as meeting the requirements of ISO 9001: 2008.
- 22.3 The environmental management system of Sto AG has been assessed and registered as meeting the requirements of ISO 14001: 2004.
- 22.4 The quality of materials, components and accessories supplied by Stoanz Limited is the responsibility of Stoanz Limited.
- 22.5 Quality on site is the responsibility of the Stoanz Limited approved applicator.
- 22.6 Designers are responsible for the building design, and building contractors are responsible for the quality of installation of framing systems and joinery, building wraps, flashing tapes, airseals, joinery head flashings and cavity battens in accordance with the instructions of Stoanz Limited.
- 22.7 Sub trades are responsible for the installation of penetrations, flashings etc that are relevant to their trade in accordance with the StoStucco Plaster Cavity System Technical Literature.
- 22.8 Building owners are responsible for the maintenance of StoStucco Plaster Cavity System in accordance with the instructions of Stoanz Limited.

Sources of Information

- AS/NZS 1170: 2002 Structural design action - General principles.
- AS/NZS 4680: 2006 Hot-dip galvanised (zinc) coatings on fabricated ferrous articles.
- NZS 3602: 2003 Timber and wood-based products for use in building.
- NZS 3603: 1993 Timber Structures Standard.
- NZS 3604: 2011 Timber-framed buildings.
- NZS 4211: 2008 Specification for performance of windows.
- Compliance Document for New Zealand Building Code External Moisture Clause E2, Department of Building and Housing, Third Edition July 2005 [Amendment 5, 1 August 2011].
- Ministry of Business, Innovation and Employment Record of Amendments for Compliance Documents and Handbooks.
- The Building Regulations 1992.



Amendments

Amendment No. 1, dated 19 December 2008.

This Appraisal has been amended to include current cone calorimeter test results for the StoStucco Plaster System.

Amendment No. 2, dated 31 January 2012.

This Appraisal has been amended to update clause changes as required by the introduction of NZS 3604: 2011 and NZBC Acceptable Solution E2/AS1 Third Edition, Amendment 5.

Amendment No. 3, dated 3 September 2013.

This Appraisal has been amended to update clause changes as required by the introduction of NZBC Fire Clauses C1 – C6 Protection from Fire and A3 Building Importance Levels.

Amendment No. 4, dated 11 November 2015.

This Appraisal has been amended to update the Appraisal Holders contact details.




In the opinion of BRANZ, **StoStucco Plaster Cavity System** is fit for purpose and will comply with the Building Code to the extent specified in this Appraisal provided it is used, designed, installed and maintained as set out in this Appraisal.

The Appraisal is issued only to **Stoanz Limited**, and is valid until further notice, subject to the Conditions of Appraisal.

Conditions of Appraisal

1. This Appraisal:
 - a) relates only to the product as described herein;
 - b) must be read, considered and used in full together with the Technical Literature;
 - c) does not address any Legislation, Regulations, Codes or Standards, not specifically named herein;
 - d) is copyright of BRANZ.
2. **Stoanz Limited**:
 - a) continues to have the product reviewed by BRANZ;
 - b) shall notify BRANZ of any changes in product specification or quality assurance measures prior to the product being marketed;
 - c) abides by the BRANZ Appraisals Services Terms and Conditions.
 - d) Warrants that the product and the manufacturing process for the product are maintained at or above the standards, levels and quality assessed and found satisfactory by BRANZ pursuant to BRANZ's Appraisal of the product.
3. BRANZ makes no representation or warranty as to:
 - a) the nature of individual examples of, batches of, or individual installations of the product, including methods and workmanship;
 - b) the presence or absence of any patent or similar rights subsisting in the product or any other product;
 - c) any guarantee or warranty offered by **Stoanz Limited**.
4. Any reference in this Appraisal to any other publication shall be read as a reference to the version of the publication specified in this Appraisal.
5. BRANZ provides no certification, guarantee, indemnity or warranty, to **Stoanz Limited** or any third party.

For BRANZ



Chris Preston
Chief Executive
Date of Issue:
29 April 2008