



BRANZ Appraised

Appraisal No. 847 [2019]

BGC STRATUM™ AND STRATUM™ DUO CAVITY CLADDING SYSTEMS

Appraisal No. 847 [2019]

This Appraisal replaces BRANZ Appraisal No. 847 [2013]

Amended 28 March 2023



BRANZ Appraisals

Technical Assessments of products for building and construction.



Appraisal Holder:

BGC (Australia) Pty Ltd

Marketed by:

BGC Fibre Cement

PO Box 76695
Manukau City
Auckland

Free Phone: 0800 424 234

Tel: 09 273 1457

Fax: 09 273 1461

Email: nz@bgc.com.au

Web: www.bgcinnovadesign.co.nz



BRANZ

BRANZ

1222 Moonshine Rd,
RD1, Porirua 5381
Private Bag 50 908
Porirua 5240,
New Zealand
Tel: 04 237 1170
branz.co.nz



Product

- 1.1 BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems are designed to be used as cavity-based, external wall cladding systems for residential and light commercial type buildings where domestic construction techniques are used.
- 1.2 BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems consist of Stratum™ and Stratum™ Duo fibre cement planks, adhesive and brad-fixed over structural timber battens to form a cavity. The fibre cement planks are finished with an acrylic paint system.
- 1.3 The system incorporates a primary and secondary means of weather resistance (first and second line of defence) against water penetration by separating the cladding from the external wall framing with a nominal 20 mm cavity.

Scope

- 2.1 The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems have been appraised as an external wall cladding system for buildings within the following scope:
 - the scope limitations of NZBC Acceptable Solution E2/AS1, Paragraph 1.1; and,
 - constructed with timber framing complying with the NZBC; and,
 - with a risk score of 0-20, calculated in accordance with NZBC Acceptable Solution E2/AS1, Table 2; and,
 - situated in NZS 3604 Wind Zones up to, and including, Extra High.
- 2.2 The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems have also been appraised for weathertightness and structural wind loading when used as an external wall cladding system for buildings within the following scope:
 - the scope limitations of NZBC Acceptable Solution E2/AS1, Paragraph 1.1 with regards to building height and floor plan area; and,
 - constructed with timber framing complying with the NZBC; and,
 - situated in specific design wind pressures up to a maximum design differential ultimate limit state [ULS] of 2.5 kPa.
- 2.3 BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems must only be installed horizontally on vertical surfaces.
- 2.4 BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems have been appraised for use with aluminium window and door joinery that is installed with vertical jambs and horizontal heads and sills. *[Note: The Appraisal of the BGC Stratum™ and Stratum™ Duo Cavity Facade Systems will rely on the joinery meeting the requirements of NZS 4211 for the relevant Wind Zone or wind pressure.]*



Building Regulations

New Zealand Building Code (NZBC)

3.1 In the opinion of BRANZ, BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems, if designed, used, installed and maintained in accordance with the statements and conditions of this Appraisal, will meet the following provisions of the NZBC:

Clause B1 STRUCTURE: Performance B1.3.1, B1.3.2, and B1.3.4. BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems meet the requirements for loads arising from self-weight, earthquake, wind and impact [i.e. B1.3.3 (a), (f), (h) and (j)]. See Paragraphs 9.1-9.4.

Clause B2 DURABILITY: Performance B2.3.1 (b) 15 years and B2.3.2. BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems meet these requirements. See Paragraphs 10.1-10.4.

Clause E2 EXTERNAL MOISTURE: Performance E2.3.2. BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems meet this requirement. See Paragraphs 14.1-14.5.

Clause F2 HAZARDOUS BUILDING MATERIALS: Performance F2.3.1. BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems meet this requirement.

Technical Specification

4.1 System components and accessories for the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems supplied by BGC [Australia] Pty Ltd are:

BGC Stratum™ and Stratum™ Duo Planks

- BGC Stratum™ and Stratum™ Duo are 12 mm thick fibre cement planks, manufactured from BGC standard fibre cement formulation. The planks are formed, cut to length, and then cured by high pressure autoclaving. The planks are profiled with a lap joint on the top and bottom edges. The BGC Stratum™ Duo planks also incorporate a 6 mm deep by 16 mm wide groove at mid plank width. The plank is coated on the front face and four edges with a sealer and a primer. BGC Stratum™ and Stratum™ Duo planks are available in a width of 300 mm and 4,200 mm long. The planks are manufactured to conform to the requirements of AS/NZS 2908.2.

Accessories

- **BGC Edge Sealer** - acrylic sealer supplied in a 400 g can to seal cut edges of BGC Stratum™ and Stratum™ Duo planks prior to installation.
 - **External and internal corners** - aluminium external box corner and 90° internal 'W' corner. The corners are available in 3,000 mm lengths.
 - **'J' flashing** - aluminium 'J' flashing, available in 2,400 mm lengths.
- 4.2 System components and accessories for the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems, which are supplied by the building contractor are:
- **Structural cavity battens** - nominal 50 mm wide by 25 mm thick (minimum finished size of 45 mm wide by 18 mm thick) SG8 framing grade pinus radiata, treated to Hazard Class H3.1.
 - **Flexible wall underlay** - building paper complying with NZBC Acceptable Solution E2/AS1, Table 23, or breather-type membranes covered by a valid BRANZ Appraisal for use as a wall underlay.
 - **Flexible wall underlay support** - polypropylene strap at 300 mm centres fixed horizontally and drawn taut for securing the building wrap in place and preventing bulging of the bulk insulation into the drainage cavity where cavity battens are installed at greater than 450 mm centres. *[Note: Additional vertical battens may also be installed to provide support.]*
 - **Rigid wall underlays** - minimum 7 mm thick H3 treated plywood or 6 mm thick fibre cement complying with NZBC Acceptable Solution E2/AS1, Table 23, or rigid air barrier systems covered by a valid BRANZ Appraisal such as BGC Durabarrier™, which is covered by BRANZ Appraisal No. 721.
 - **Flexible sill and jamb flashing tape** - flexible flashing tapes complying with NZBC Acceptable Solution E2/AS1, Paragraph 4.3.11, or flexible flashing tapes covered by a valid BRANZ Appraisal for use around window and door joinery openings.



- **Cavity vent strip** - PVC, aluminium or stainless steel, punched with 3-5 mm holes or slots complying with NZBC Acceptable Solution E2/AS1, Paragraph 9.1.8.3.
- **Window and door trim cavity air seal** - air seals and PEF rod complying with NZBC Acceptable Solution E2/AS1, Paragraph 9.1.6, or self-expanding, moisture cure polyurethane foam air seals covered by a valid BRANZ Appraisal for use around window, door and other wall penetration openings.
- **Flexible sealant** - sealant complying with NZBC Acceptable Solution E2/AS1, or sealant covered by a valid BRANZ Appraisal for use as a weather sealing sealant for exterior use.
- **Gap filler** - Bostik MS Safe Seal, coloured white where vertical gaps are to be painted, or sealant/gap filler covered by a valid BRANZ Appraisal for use as a weather sealing sealant for exterior use.
- **Aluminium joinery head flashing** - as supplied by the joinery manufacturer or the contractor.
- **Flashings** - balustrade and parapet cap flashings, and inter-storey joint flashings. Refer to NZS 3604, Section 4, and NZBC Acceptable Solution E2/AS1, Table 20 for durability requirements.
- **Cavity batten fixings** - 65 x 2.8 mm Paslode RounDrive®, ring shank galvanised nails.

Plank fixing

- **Plank nail fixings** - 30 x 1.6 mm or 40 x 2 mm stainless steel brad nails. *[Note: Stainless steel must be Grade 304 or 316.]*
- **Adhesive Sealant** - Bostik Seal N' Flex Facade, for fixing BGC Stratum™ and Stratum™ Duo planks to the cavity battens.

Paint System Specification

- 4.3 Paint systems are not supplied by BGC [Australia] Pty Ltd and have not been assessed by BRANZ and are therefore outside the scope of this Appraisal.
- 4.4 All exposed faces and edges of BGC Stratum™ and Stratum™ Duo planks and cavity battens must be finished with at least two coats of an exterior grade latex acrylic paint system complying with any of Parts 7, 8, 9 or 10 of AS 3730.

Handling and Storage

- 5.1 Handling and storage of all materials supplied by BGC [Australia] Pty Ltd or the building contractor, whether on-site or off-site, is under the control of the building contractor. BGC Stratum™ and Stratum™ Duo planks must be stacked flat, off the ground and supported on a level platform. They must be kept dry at all times either by storing under cover or by providing waterproof covers to the stack. Care must be taken to avoid damage to edges and surfaces. The planks must always be carried on edge.
- 5.2 Cavity battens and other accessories must be stored so they are kept clean, dry and undamaged. All accessories must be used within the maximum storage period recommended by the manufacturer.

Technical Literature

- 6.1 This Appraisal must be read in conjunction with:
- Stratum™, Stratum™ Duo, Stratum™ Trio – Horizontal and Vertical Installation Stratum™ Contour, June 2021.
 - BGC Stratum Architectural Drawings ST-01 to ST-31, all dated January 2014.
 - BGC Stratum Architectural Drawings ST-33 to ST-36, all dated May 2019.
- 6.2 All aspects of design, use, installation and maintenance contained within the Technical Literature and within the scope of this Appraisal must be followed.



Design Information

Framing

Timber Treatment

- 7.1 Timber wall framing behind the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems must be treated as required by NZBC Acceptable Solution B2/AS1.

Timber Framing

- 7.2 Timber framing must comply with NZS 3604 for buildings or parts of buildings within the scope limitations of NZS 3604. Buildings or parts of buildings outside the scope of NZS 3604 must be to a specific design in accordance with NZS 3603 and AS/NZS 1170. Where specific design is required, the framing must be of at least equivalent stiffness to the framing provisions of NZS 3604. In all cases, studs must be at maximum 600 mm centres. Dwangs must be fitted flush between the studs at maximum 800 mm centres.
- 7.3 Timber framing must have a maximum moisture content of 20% at the time of the application of BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems. *[Note: If the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems are fixed to framing with a moisture content of greater than 20%, problems may occur at a later date due to excessive timber shrinkage.]*

Cavity Battens

- 7.4 The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems incorporates vertical cavity battens which form the nominal 20 mm cavity behind the BGC Stratum™ and Stratum™ Duo planks.

BGC Stratum™ and Stratum™ Duo Plank Set Out

- 7.5 All BGC Stratum™ and Stratum™ Duo plank end joints must be made over a stud. At the base of the wall, the planks must hang 50 mm below the supporting framing.
- 7.6 Additional framing may be required at soffits, internal and external corners and window and door openings for the support and fixing of plank ends.

General

- 8.1 When the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems are used for specifically designed buildings up to 2.5 kPa ULS wind pressure, only the weathertightness aspects of the cladding and BGC Stratum™ and Stratum™ Duo plank fixing centres are within the scope of this Appraisal. All other aspects of the building need to be specifically designed and are outside the scope of this Appraisal.
- 8.2 Punchings in the cavity vent strip must provide a minimum ventilation opening area of at least 1,000 mm² per lineal metre of wall in accordance with NZBC Acceptable Solution E2/AS1, Paragraph 9.1.8.3 b].
- 8.3 At ground level, the bottom edge of the BGC Stratum™ and Stratum™ Duo planks must be kept clear of paved surfaces, such as footpaths, by a minimum of 100 mm and unpaved surfaces by 175 mm in accordance with NZBC Acceptable Solution E2/AS1, Table 18. The ground clearances to finished floor levels as set out in NZS 3604 must be adhered to.
- 8.4 At balcony, deck or low pitched roof/wall junctions, the bottom edge of the BGC Stratum™ and Stratum™ Duo planks must be kept clear of any adjacent surface, or above the top surface of any adjacent roof flashing by a minimum of 35 mm in accordance with NZBC Acceptable Solution E2/AS1, Paragraph 9.1.3.6.



- 8.5 All external walls of buildings must have barriers to airflow in the form of flexible wall underlays and interior linings with all joints stopped for Wind Zones up to, and including, Very High, and rigid wall underlays for buildings in the Extra High Wind Zone and specifically designed buildings up to 2.5 kPa design differential ULS wind pressure. Unlined gables and walls must incorporate a rigid sheathing or an air barrier [e.g. BGC Durabarrier™] which meets the requirements of NZBC Acceptable Solution E2/AS1, Table 23. For attached garages, wall underlays must be selected in accordance with NZBC Acceptable Solution E2/AS1, Paragraph 9.1.3.4. Where rigid underlays are used, the cavity batten fixing lengths must be increased by a minimum of the thickness of the underlay.
- 8.6 Where penetrations through the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems are wider than the cavity batten spacing, allowance must be made for airflow between adjacent cavities. A minimum 10 mm gap must be left between the bottom of the vertical cavity batten and the flashing to the opening.
- 8.7 Where the system abuts other cladding systems, designers must detail the junction to meet their own requirements and the performance requirements of the NZBC. Details not included in the Technical Literature have not been assessed and are outside the scope of this Appraisal.

Inter-storey Junctions

- 8.8 Inter-storey junctions must be constructed in accordance with the Technical Literature. Inter-storey joints must be provided to limit continuous cavities to the lesser of 2-storeys or 7 m in height, in accordance with the requirements of NZBC Acceptable Solution E2/AS1, Paragraph 9.1.9.4 b).

Structure

Mass

- 9.1 The mass of the BGC Stratum™ planks when installed on the wall is 15 kg/m² at equilibrium moisture content (EMC) and BGC Stratum™ Duo is 14.7 kg/m². The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems are therefore considered as light wall claddings in terms of NZS 3604.

Impact Resistance

- 9.2 BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems have good resistance to impacts likely to be encountered in normal residential use. The likelihood of impact damage to the system when used in light commercial situations should be considered at the design stage, and appropriate protection such as the installation of bollards and barriers should be considered for vulnerable areas.

Wind Zones

- 9.3 The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems are suitable for use in all Wind Zones of NZS 3604 up to, and including, Extra High where buildings are designed to meet the requirements of NZBC Acceptable Solution E2/AS1, Paragraph 1.1, or up to 2.5 kPa design differential ULS wind pressure where buildings are specifically designed.

Plank Fixing

- 9.4 The planks must be mechanically fixed with 30 mm long stainless steel brads in conjunction with the adhesive sealant [refer to Paragraph 17.7]. The planks are fastened at each stud to the cavity batten with a brad positioned 50 mm up from the bottom of the plank and a brad positioned 20 mm down from the top of the plank. The adhesive sealant is placed as a continuous bead to the batten.



Durability

Serviceable Life

- 10.1 BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems installations are expected to have a serviceable life of at least 30 years provided the paint coating to the BGC Stratum™ and Stratum™ Duo planks is maintained in accordance with this Appraisal, and the BGC Stratum™ and Stratum™ Duo planks and fixings are continuously protected by a weathertight coating and remain dry in service. BGC Stratum™ and Stratum™ Duo planks must be painted and the exposed sections of the cavity battens at expressed joints must be sealed with a minimum 2 mm deep bead of gap filler within three months of installation.
- 10.2 Coastal locations can be very corrosive to fasteners, especially locations within distances of up to 500 m from the sea including harbours, or 100 m from tidal estuaries and sheltered inlets, and otherwise as shown in NZS 3604, Figure 4.2. These coastal locations are defined in NZS 3604 as Zone D. To achieve an extended serviceable life in Zone D, structural battens must be fixed with stainless steel or protected hot-dip galvanised steel fasteners. Batten fixings outside Zone D may be hot-dip galvanised steel. BGC Stratum™ and Stratum™ Duo planks must always be fixed with stainless steel brads.
- 10.3 Microclimatic conditions, including geothermal hot spots, industrial contamination and corrosive atmospheres, and contamination from agricultural chemicals or fertilisers can convert mildly corrosive atmosphere into aggressive environments for fasteners. The fixing of structural battens and BGC Stratum™ and Stratum™ Duo planks in areas subject to microclimatic conditions requires specific design in accordance with NZS 3604, Paragraph 4.2.4, and is outside the scope of this Appraisal.

Maintenance

- 11.1 Regular maintenance is essential to ensure the performance requirements of the NZBC are continually met and to ensure the maximum serviceability of the system.
- 11.2 Regular cleaning [at least annually] of the paint coating is recommended to remove grime, dirt and organic growth, to maximise the life and appearance of the coating. Grime may be removed by brushing with a soft brush, warm water and detergent.
- 11.3 Paint systems must be recoated at approximately 5-10 year intervals in accordance with the paint manufacturer's instructions.
- 11.4 Annual inspections must be made to ensure that all aspects of the cladding system, including the paint coating system, flashings and any sealed joints remain in a weatherproof condition. The planks must be checked to ensure the fixings and adhesive bond are sound. Any damaged areas or areas showing signs of deterioration which would allow water ingress must be repaired immediately. Sealant and paint coatings must be repaired in accordance with the relevant manufacturer's instructions.
- 11.5 Minimum ground clearances as set out in this Appraisal and the Technical Literature must be maintained at all times during the life of the cladding. *[Note: Failure to adhere to the minimum ground clearances given in this Appraisal and the Technical Literature will adversely affect the long term durability of the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems.]*

Control of External Fire Spread

Vertical Fire Spread

- 12.1 This Appraisal only covers buildings 10 m or less in height. NZBC Functional Requirement C3.2 identifies that external vertical fire spread to upper floors only needs be considered for buildings with a building height greater than 10 m. Control of external vertical fire spread is therefore outside the scope of this Appraisal.



Horizontal Fire Spread

- 12.2 The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems has a peak heat release rate of less than 100 kW/m² and a total heat released of less than 25 MJ/m². Testing was carried out as per Paragraph 5.4 of NZBC Acceptable Solution C/AS1 and Paragraph 5.8.1 of NZBC Acceptable Solution C/AS2, achieving a Type A performance. The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems can therefore be used within 1 m of the relevant boundary.
- 12.3 Refer to NZBC Acceptable Solutions C/AS1 and C/AS2 and Verification Method C/VM2 for fire resistance rating and control of external fire spread requirements for external walls.

Prevention of Fire Occurring

- 13.1 When BGC Stratum™ and Stratum™ Duo planks are finished with a paint coating of not more than 1 mm in thickness, clearance separations from heat sources such as fireplaces, heating appliances, flues and chimneys are not required. However when used in conjunction with, or attached to heat sensitive materials, the heat sensitive materials must be separated from heat sources such as fireplaces, heating appliances and chimneys. Part 7 of NZBC Verification Method C/VM1 and Acceptable Solution C/AS1, and NZBC Acceptable Solution C/AS2 provide methods for separation and protection of combustible materials from heat sources.

External Moisture

- 14.1 The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems, when installed and maintained in accordance with this Appraisal and the Technical Literature will prevent the penetration of moisture that could cause undue dampness or damage to building elements.
- 14.2 The cavity must be sealed off from the roof and subfloor spaces to meet compliance with NZBC Clause E2.3.5.
- 14.3 The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems allows excess moisture present at the completion of construction to be dissipated without permanent damage to building elements to meet compliance with NZBC Clause E2.3.6.
- 14.4 The details given in the Technical Literature for weather sealing are based on the principles of having a first and second line of defence against moisture entry for all joints, penetrations and junctions. The ingress of moisture must be excluded by detailing joinery and wall interfaces as shown in the Technical Literature. Weathertightness details that are developed by the designer are outside the scope of this Appraisal and are the responsibility of the designer for compliance with the NZBC.
- 14.5 The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems, where there is a designed cavity drainage path for moisture that penetrates the cladding, does not reduce the requirement for joints, penetrations etc. to remain weather-resistant.

Internal Moisture

- 15.1 Buildings must be constructed with an adequate combination of thermal resistance and ventilation, and space temperature must be provided to all habitable spaces, laundries and other spaces where moisture may be generated or may accumulate.

Water Vapour

- 15.2 BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems are not a barrier to the passage of water vapour, and when installed in accordance with this Appraisal will not create a risk of moisture damage resulting from condensation.



Installation Information

Installation Skill Level Requirements

- 16.1 Installation of BGC Stratum™ and Stratum™ Duo and accessories supplied by BGC [Australia] Pty Ltd and the building contractor must always be carried out in accordance with the BGC Stratum™ and Stratum™ Duo Technical Literature and this Appraisal by, or under the supervision of a Licensed Building Practitioner [LBP] with the relevant Licence Class.

System Installation

Building Underlay and Flexible Sill and Jamb Tape Installation

- 17.1 The selected building underlay and flexible sill and jamb tape system must be installed by the building contractor in accordance with the underlay and tape manufacturer's instructions prior to the installation of the cavity battens and the rest of the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems. Flexible building underlay must be installed horizontally and be continuous around corners. Underlay must be lapped 75 mm minimum at horizontal joints and 150 mm minimum over studs at vertical joints. Generic rigid sheathing materials must be installed in accordance with NZBC Acceptable Solution E2/AS1 and be overlaid with a flexible wall underlay. Proprietary systems (e.g. BGC Durabarrier™) shall be installed in accordance with the manufacturer's instructions. Particular attention must be paid to the installation of the building underlay and sill and jamb tapes around window and door openings to ensure a continuous seal is achieved and all exposed wall framing in the opening is protected.
- 17.2 Where studs are at greater than 450 mm centres and a flexible wall underlay is being used, a building underlay support must be installed over the underlay at maximum 300 mm centres horizontally.

Cavity Battens

- 17.3 Cavity battens must be installed vertically over the building underlay to the wall studs at maximum 600 mm centres where the studs are at 600 mm centres, or at 400 mm centres when studs are at 400 mm centres. The battens must be fixed in place with 65 x 2.8 mm Paslode RoundDrive®, ring shank galvanised nails, at maximum 300 mm centres alternately offset from the centre line by 12 mm. Where a rigid underlay is used, the length of the nail must be increased by a minimum of the thickness of the underlay.

Aluminium Joinery Installation

- 17.4 Aluminium joinery and associated head flashings must be installed by the building contractor in accordance with the Technical Literature. A nominal 10 mm gap must be left between the joinery reveal and the wall framing so a PEF rod and air seal can be installed after the joinery has been secured in place.

BGC Stratum™ and Stratum™ Duo Plank Installation

- 17.5 BGC Stratum™ and Stratum™ Duo planks may be cut using either hand or power tools. Holes and cut-outs may be formed by drilling a number of holes around the perimeter of the opening required and tapping out the centre with a hammer, or by using a hole saw.
- 17.6 BGC Stratum™ and Stratum™ Duo planks must be dry prior to installation. Cut edges must be sealed with BGC Edge Sealer, prior to sheet installation.

BGC Stratum™ and Stratum™ Duo Plank Fixing

- 17.7 BGC Stratum™ and Stratum™ Duo planks and cavity battens must be dry and free of dust, prior to application of the Bostik Seal N' Flex Facade. The adhesive sealant must not be applied at temperatures below 5°C. Bostik Seal N' Flex Facade is applied in a continuous 6 mm bead to the cavity battens as described in the Technical Literature. In addition, BGC Stratum™ and Stratum™ Duo planks must be fixed to the cavity battens with brads. Each plank is fixed with a brad 50 mm up from the bottom of the plank and a second brad in the lap of the plank. The brads must be positioned a minimum of 10 mm from all plank ends.

Finishing

- 17.8 Brad holes must be filled with a suitable epoxy filler and sanded flush.
- 17.9 Vertical express joints must be filled with 2-3 mm of gap filler.
- 17.10 The BGC Stratum™ and Stratum™ Duo planks must be finished with a paint coating system that will protect it from moisture. A latex exterior paint system complying with any of parts 7, 8, 9 or 10 of AS 3730 is suitable.
- 17.11 The paint coating manufacturer's instructions must be followed at all times for application of the paint finish. BGC Stratum™ and Stratum™ Duo planks must be dry before commencing painting.

Inspection

- 17.12 The Technical Literature must be referred to during the inspection of BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems installations.

Health and Safety

- 18.1 Safe use and handling procedures for the components that make up the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems are provided in the manufacturer's Technical Literature.
- 18.2 Cutting of BGC Stratum™ and Stratum™ Duo planks must be carried out in well ventilated areas, and a dust mask and eye protection must be worn. When power tools are used for cutting, grinding or forming holes, safety measures as set out in the Technical Literature must be undertaken because of the amount of dust generated.

Basis of Appraisal

The following is a summary of the technical investigations carried out:

Tests

- 19.1 Wind face load testing for the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems was completed by BRANZ. BRANZ determined design wind suction pressures, and by comparing these with the NZS 3604 design wind speeds and AS/NZS 1170 pressure coefficients, the fixing requirements were determined for timber-framed walls.
- 19.2 BRANZ expert opinion on NZBC E2 code compliance for the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems was based on testing and evaluation of all details within the scope and as stated within this Appraisal. The BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems were tested to the version of E2/VM1 contained within the NZBC Clause E2 Amendment 5. The testing assessed the performance of the foundation detail, window head, jamb and sill details, meter box head, jamb and sill details, vertical and horizontal joints, internal and external corners. In addition to the weathertightness test, the details contained within the Technical Literature have been reviewed, and an opinion has been given by BRANZ technical experts that the system will meet the performance levels of NZBC Acceptable Solution E2/AS1 for drained cavity claddings.
- 19.3 Cone calorimeter testing to determine the peak rate of heat release and total heat release of BGC NuLine weatherboard was completed by BRANZ and the results were used to provide an assessment of the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems. The testing was carried out in accordance with AS/NZS 3837.

Other Investigations

- 20.1 Structural, durability and fire opinions have been given by BRANZ technical experts.
- 20.2 Site inspections have been carried out by BRANZ to assess the practicability of installation, and to examine completed installations.
- 20.3 The Technical Literature for the BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems have been examined by BRANZ and found to be satisfactory.



Quality

- 21.1 The manufacture of BGC Stratum™ and Stratum™ Duo planks has been examined by BRANZ, including the methods for quality control. Details regarding the quality and composition of the materials used were obtained by BRANZ and found to be satisfactory.
- 21.2 The quality of materials, components and accessories supplied by BGC [Australia] Pty Ltd is the responsibility of BGC [Australia] Pty Ltd.
- 21.3 The quality management system of the manufacturer of BGC Stratum™ and Stratum™ Duo planks, BGC [Australia] Pty Ltd, has been assessed and registered as meeting the requirements of ISO 9001.
- 21.4 Quality of installation on-site of components and accessories supplied by BGC [Australia] Pty Ltd and the building contractor is the responsibility of the installer.
- 21.5 Designers are responsible for the building design, and building contractors are responsible for the quality of installation of framing systems and joinery, wall underlays, flashing tapes, air seals, joinery head flashings, cavity battens and BGC Stratum™ and Stratum™ Duo planks in accordance with the instructions of BGC [Australia] Pty Ltd.
- 21.6 Building owners are responsible for the maintenance of BGC Stratum™ and Stratum™ Duo Cavity Cladding Systems in accordance with the instructions of BGC [Australia] Pty Ltd.

Sources of Information

- AS 3730 Guide to the properties of paints for buildings.
- AS/NZS 1170 Structural design actions.
- AS/NZS 2908.2:2000 Cellulose-cement products - Flat sheet.
- AS/NZS 3837:1998 Method of test for heat and smoke release rates for materials and products using an oxygen consumption calorimeter.
- AS/NZS 4680:2006 Hot-dip galvanised [zinc] coatings on fabricated ferrous articles.
- NZS 3604:2011 Timber-framed buildings.
- NZS 4211:2008 Specification for performance of windows.
- Ministry of Business, Innovation and Employment Record of amendments - Acceptable Solutions, Verification Methods and handbooks.
- The Building Regulations 1992.

Amendments

Amendment No. 1, dated 06 August 2021.

This appraisal has been amended to reflect building code updates relating to fire.

Amendment No. 2, dated 28 March 2023.

This appraisal has been amended to update the Technical Literature.



BRANZ Appraised
Appraisal No. 847 [2019]

BRANZ Appraisal
Appraisal No. 847 [2019]
23 May 2019

BGC STRATUM™ AND
STRATUM™ DUO CAVITY
CLADDING SYSTEMS



In the opinion of BRANZ, **BGC Stratum™ and Stratum™ Duo Cladding Cavity Systems** are fit for purpose and will comply with the Building Code to the extent specified in this Appraisal provided they are used, designed, installed and maintained as set out in this Appraisal.

The Appraisal is issued only to **BGC [Australia] Pty Ltd**, and is valid until further notice, subject to the Conditions of Appraisal.

Conditions of Appraisal

1. This Appraisal:
 - a) relates only to the product as described herein;
 - b) must be read, considered and used in full together with the Technical Literature;
 - c) does not address any Legislation, Regulations, Codes or Standards, not specifically named herein;
 - d) is copyright of BRANZ.
2. **BGC [Australia] Pty Ltd**:
 - a) continues to have the product reviewed by BRANZ;
 - b) shall notify BRANZ of any changes in product specification or quality assurance measures prior to the product being marketed;
 - c) abides by the BRANZ Appraisals Services Terms and Conditions;
 - d) warrants that the product and the manufacturing process for the product are maintained at or above the standards, levels and quality assessed and found satisfactory by BRANZ pursuant to BRANZ's Appraisal of the product.
3. BRANZ makes no representation or warranty as to:
 - a) the nature of individual examples of, batches of, or individual installations of the product, including methods and workmanship;
 - b) the presence or absence of any patent or similar rights subsisting in the product or any other product;
 - c) any guarantee or warranty offered by **BGC [Australia] Pty Ltd**.
4. Any reference in this Appraisal to any other publication shall be read as a reference to the version of the publication specified in this Appraisal.
5. BRANZ provides no certification, guarantee, indemnity or warranty, to **BGC [Australia] Pty Ltd** or any third party.

For BRANZ

Chelydra Percy

Chief Executive

Date of Issue:

23 May 2019